

DEGADUR® 332 AND DEGADUR® 530 FOR ELASTIC INDUSTRIAL FLOORS, INDOORS AND OUTDOORS

General Description

Under the DEGADUR® trademark, Röhm produces rapidly curing methacrylic resins that are used to formulate floor coatings, with the addition of fillers and pigments. Their rapid curing (even at temperatures as low as minus 30°C) ensures very short interruptions in routine operations. The coatings can be used to provide smooth or textured surfaces. Seamless DEGADUR® industrial floor coatings are robust and resistant to many conventional chemicals such as acids and alkalis. The degree of mechanical strength and slip resistance can be precisely adjusted according to the specific requirements or relevant industrial regulations. Individual wishes can be met in terms of color or design. DEGADUR® coating systems can generally be applied on concrete and metal substrates, asphalt, indoor and outdoor areas as well as in wet and dry rooms.

Functional systems for highly weather-resistant elastic floors

Coatings based on DEGADUR® 332, sealed with DEGADUR® 530, are especially suitable for elastic indoor and outdoor surfaces. This coating of at least 5 mm thickness must always be broadcast. The particle size and type of broadcast material determine the mechanical strength, field of application, color, texture and slip resistance of the coating.

Summary of benefits

- Rapid curing - floor can be used and exposed to normal loads after two hours, which means minimal downtimes
- Coating possible at ambient temperatures of -30°C to +35°C
- Good wear resistance
- Seamless and water-tight
- Good chemical resistance to acids, alkalis and many cleaning agents
- New DEGADUR® coatings can be applied to old DEGADUR® substrates

DEGADUR® 332/530 – for custom-tailored system solutions

- Extremely elastic floor coating with high UV resistance
- Impact-resistant and crack-bridging
- For high mechanical loads on indoor and outdoor surfaces
- For application on substrates of low mechanical strength

Fields of application

- Warehouses
- Cold storage rooms and deep-freeze stores; combined with DEGADUR® 430, also in shock frosters
- Metalworking industry
- Multistory car parks
- Printing shops, workshops
- Loading ramps
- Bridge and road coatings

Substrate Composition

The substrate must be correctly prepared for coating as described below. The primer must be allowed to cure properly on the substrate in order to guarantee a durable bond. This applies equally to concrete, asphalt and metal substrates and to old coatings.

The surfaces must be solid, dry, offer good grip and be capable of bearing loads. They must be free from laitance, loose particles, flakiness and substances like grease, oil, rubber fines, paint residues or other contaminants that would prevent bonding.

The best floor preparation is usually achieved by means of shotblasting or mechanical removal (grinding). For very soiled surfaces, these mechanical methods can be advantageously combined with flame paring. After preparing the substrate, its pull-off strength must be at least 1.5 N/mm². Tensile bond measurements can be performed using a Herion appliance, for example A simple adhesive test patch with the chosen primer, e.g. DEGADUR® 112, may provide an indication of how well the floor has been prepared.

The floor-laying company must furnish proof of adequate adhesion!

Since it is very important to correctly prepare and assess the substrate, we recommend that you consult the Technical Information Sheet "Substrate Analysis and Floor Preparation for Coating Work with DEGADUR® Systems."

Maximum substrate humidity

Substrate	Ambient humidity (before and after coating)
Reinforced concrete floor	2.0–3.0%
Pumice concrete	3.0–5.0%
Cementitious screed, depending on mixing ratio	1.5–3.0%
Aerated concrete screed, cement-bound	2.5–3.5%
Cold bitumen screed, cement-bound	1.5–2.0%
Magnesia flooring	8.5–12.0%
Anhydride and gypsum screeds	less than 0.5%
Chipboard, hardboard, wooden floors	8.0–12.0%

Primer

The primer DEGADUR® B 71 or DEGADUR® 112 is mixed with the corresponding amount of BPO hardener powder by stirring, distributed on the substrate using a rubber blade and rolled out in an evenly thin layer (400 – 500 g/m²). Highly absorbent substrates are coated with primer twice to ensure that a thin, continuous film exists over the entire surface to bind the broadcast material. The primer is lightly broadcast with quartz sand (Ø 0.4 - 0.8mm). This process takes little time but guarantees an ideal bond between the primer and the coating.

BPO hardener quantities for DEGADUR® 112 primer

Temperature [°C]*)	Hardener [w/w %] **)	Pot life [min]	Curing time [min]
+5	5	appr. 8	appr. 30
+10	4	appr. 8	appr. 30
+15	3	appr. 7	appr. 30
+20	2	appr. 8	appr. 30
>30	1	appr. 6.5	appr. 30

*) The temperature refers to the resin, floor and air temperature

***) The hardener quantities refer to DEGADUR® 112; for DEGADUR® B 71, see data sheet

Note: The stated values are based on laboratory tests. In practice, external influences may lead to deviations from these values.

Coating

Coatings with DEGADUR® 332 are characterized by their good self-leveling properties. Owing to its high mechanical strength, DEGADUR® 332 is the preferred choice for coatings with layer thicknesses of 5-8mm. Mixed with DEGADUR® 430, it is also suitable for coating floors in deep-freeze stores, according to the relevant technical information sheets. The typical material consumption, according to filler type, is approx. 1.8 kg/m² per mm layer thickness.

Typical formulation for 5–8 mm coating

Quantity [pbw]	Product
30.0	DEGADUR® 332
30.0	Quartz powder, barite, calcite
40.0	Quartz sand 0.4–0.8mm

BPO hardener quantities for DEGADUR® 332 mortar

Temperature [°C]*)	Hardener [w/w %] **)	Pot life [min]	Curing time [min]
+5	5.0	appr. 25	appr. 70
+10	4.0	appr. 25	appr. 60
+20	2.0	appr. 20	appr. 45
+30	1.5	appr. 25	appr. 50

*) The temperature refers to the resin, floor and air temperature

***) The hardener quantities refer to DEGADUR® 332

Note: The stated values are based on laboratory tests. In practice, external influences may lead to deviations from these values.

The mixture for practical application is distributed using a pin rake. The wet film thickness must be at least 4mm. The coating is then broadcast with quartz sand of particle size 0.7–1.2 mm or 0.4–0.8mm, depending on the required surface texture.

Seal Coat

The entire quantity of DEGADUR® 529 mixed with BPO powder is poured onto the coating, distributed roughly using a rubber blade and then evenly applied with a polyamide roller (pile 12mm). It is advisable to pigment the top coat.

BPO hardener quantities for DEGADUR® 530 seal coat

Temperature [°C]*)	Hardener [w/w %] **)	Pot life [min]	Curing time [min]
+5	3.5	appr. 35	appr. 70
+10	2.5	appr. 15	appr. 40
+20	1.5	appr. 15	appr. 40
+30	1.0	appr. 13	appr. 35

*) The temperature refers to the resin, floor and air temperature

***) The hardener quantities refer to DEGADUR® 530

Note: The stated values are based on laboratory tests. In practice, external influences may lead to deviations from these values.

Important points to bear in mind for the seal coat

- To prevent yellowing, it is important to precisely observe the hardener quantities stated in the table.
- For outdoor coatings it is recommended to pigment the top coat.
- Owing to the thermoplastic nature of MMA resins, forklift traffic may leave black abrasion marks (tire marks).
- The hardener powder must be thoroughly stirred in for at least one minute.
- Good ventilation during processing ensures good curing of the seal coat.

Properties of a coating system with DEGADUR® 332 and DEGADUR® 530

Property	Standard/Test Method	Unit	Result (according to typical formulation on page 3)
Tensile strength	DIN EN ISO 527	[MPa]	4.4
Compressive strength	DIN EN ISO 604	[MPa]	14.9
Elongation at break	DIN EN ISO 527	[%]	8.8
Elastic modulus	DIN EN ISO 527	[MPa]	409.6
Tensile bond strength on concrete	DIN ISO 4624 ZTV-SIB	[MPa]	> 2.0
Impact strength	EN ISO 6272	[Nm]	4
Wear resistance according to BCA	prEN 13892-4	[µm]	< 10
Slip resistance / displacement volume	BGR 181 and DIN 51130	[R/V]	R11 / V8
Reaction to fire	EN 13501-1	[Class]	Efl
Physiological inoffensiveness	EU Regulation 1935/2004 of the European Parliament dated 27 Oct. 2004	Food Contact Declaration	(Test report No. 42964 U 16) The coating system is physiologically safe. Suitable for food processing companies.

Röhm GmbH
Deutsche-Telekom-Allee 9
64295 Darmstadt
Germany

Phone: +49 6241 402-0

degadur@roehm.com
www.degadur.com
www.roehm.com

Roehm Chemical (Shanghai) Co., Ltd.
55 Chundong Rd. Xinzhuang Industry Park
201108, Shanghai
China

Phone: +86 21 6119 1616

Roehm America LLC
299 Jefferson Road
Parsippany NJ 07054
USA

Phone: +1 973 929 8000

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

® = Registered trademark of Röhm or affiliates

DEGADUR® is a registered trademark of Röhm GmbH, Darmstadt, Germany